



Illinois Department of Transportation

2300 South Dirksen Parkway / Springfield, Illinois / 62764

September 12, 2019

SUBJECT: FAP Route 103 (IL 13/15)
Project NHPP-DZ9C(453)
Section (27, 25, 38, 561)RS
St. Clair County
Contract No. 76J16
Item No. 56, September 20, 2019 Letting
Addendum A

NOTICE TO PROSPECTIVE BIDDERS:

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

1. Revised the Table of Contents to the Special Provisions.
2. Added pages 99-101 to the Special Provisions
3. Revised sheets 46-50 of the Plans

Prime contractors must utilize the enclosed material when preparing their bid and must include any changes to the Schedule of Prices in their bid.

Very truly yours,

A handwritten signature in black ink, appearing to read 'Jack A. Elston'.

Jack A. Elston, P.E.
Bureau Chief, Design and Environment

CWR/cr

TABLE OF CONTENTS

LOCATION OF PROJECT	1
DESCRIPTION OF PROJECT	1
SUBMITTAL OF EEO/LABOR DOCUMENTATION	1
COOPERATION BETWEEN CONTRACTORS.....	4
TEMPORARY RAMPS.....	4
HOT-MIX ASPHALT MIXTURE IL-9.5FG (CBM).....	4
HOT-MIX ASPHALT.....	7
PORTLAND CEMENT CONCRETE DRIVEWAY PAVEMENT, SPECIAL.....	7
PORTLAND CEMENT CONCRETE SIDEWALK, SPECIAL.....	8
TEMPORARY SIDEWALK.....	9
HOT-MIX ASPHALT SURFACE REMOVAL W/SKETCH OF ILLINOIS STANDARD W8-I107...	9
HOT-MIX ASPHALT SURFACE REMOVAL, VARIABLE DEPTH	12
COMBINATION CURB AND GUTTER REMOVAL	12
CONCRETE STEP REMOVAL	12
VALVE BOX FRAMES TO BE ADJUSTED.....	13
COMBINATION CONCRETE CURB AND GUTTER (ABUTTING EXISTING PAVEMENT).....	13
COMBINATION CONCRETE CURB AND GUTTER, TYPE B-6.24 (MODIFIED).....	13
REMOVAL AND DISPOSAL OF REGULATED SUBSTANCES	14
REMOVAL AND DISPOSAL OF REGULATED SUBSTANCES (BDE)	15
PAINT CURB	26
RIGHT-OF-WAY AND PROPERTY CORNERS.....	27
PRESERVING SURVEY MONUMENTS.....	28
SURVEY MONUMENT COVER ASSEMBLY.....	28
TRAFFIC CONTROL PLAN	30
TRAFFIC CONTROL AND PROTECTION STANDARD 701501.....	30
CONSTRUCTION AND MAINTENANCE SIGN SUPPORTS	31
REMOVE EXISTING TRAFFIC SIGNAL EQUIPMENT	31
DETECTOR LOOP REPLACEMENT	32
PEDESTRIAN PUSH-BUTTON, SPECIAL.....	33
STATUS OF UTILITIES TO BE ADJUSTED	33

AUTOMATED FLAGGER ASSISTANCE DEVICES (BDE)	34
BITUMINOUS MATERIALS COST ADJUSTMENTS (BDE)	35
COMPENSABLE DELAY COSTS (BDE)	36
CONSTRUCTION AIR QUALITY – DIESEL RETROFIT (BDE)	40
DISADVANTAGED BUSINESS ENTERPRISE PARTICIPATION (BDE)	42
DISPOSAL FEES (BDE)	51
EMULSIFIED ASPHALTS (BDE)	52
EQUIPMENT PARKING AND STORAGE (BDE)	55
FUEL COST ADJUSTMENT (BDE)	56
GROOVING FOR RECESSED PAVEMENT MARKINGS (BDE).....	58
HOT-MIX ASPHALT – LONGITUDINAL JOINT SEALANT (BDE).....	60
HOT-MIX ASPHALT – OSCILLATORY ROLLER (BDE)	64
HOT MIX ASPHALT – QUALITY CONTROL FOR PERFORMANCE (BDE)	65
LIGHTS ON BARRICADES (BDE)	71
MATERIAL TRANSFER DEVICE (BDE)	72
PAVEMENT MARKING REMOVAL (BDE).....	73
PAYMENTS TO SUBCONTRACTORS (BDE)	74
PORTLAND CEMENT CONCRETE (BDE)	75
PREFORMED PLASTIC PAVEMENT MARKING TYPE D - INLAID (BDE).....	75
PROGRESS PAYMENTS (BDE).....	78
RECLAIMED ASPHALT PAVEMENT AND RECLAIMED ASPHALT SHINGLES (BDE)	79
SUBCONTRACTOR AND DBE PAYMENT REPORTING (BDE)	88
SUBCONTRACTOR MOBILIZATION PAYMENTS (BDE).....	88
TEMPORARY PAVEMENT MARKING (BDE).....	89
TRAINING SPECIAL PROVISIONS (BDE)	91
IDOT TRAINING PROGRAM GRADUATE ON-THE-JOB TRAINING SPECIAL PROVISION...93	
TRAFFIC CONTROL DEVICES - CONES (BDE).....	96
WARM MIX ASPHALT (BDE)	96
WEEKLY DBE TRUCKING REPORTS (BDE).....	98
WORKING DAYS (BDE)	98
PREFORMED PLASTIC PAVEMENT MARKING - TYPE D.....	99

PREFORMED PLASTIC PAVEMENT MARKING - TYPE D

Revise subparagraph (c) and add subparagraph (i) to Article 780.02 of the Standard Specifications:

- “(c) Preformed Plastic Pavement Markings, Type B and Type C..... 1095.03
- (i) Preformed Plastic Pavement Marking, Type D 1095.10”

Revise the first paragraph of Article 780.07(b) of the Standard Specifications to read:

- “(b) Type B, C, or D - Standard Application. The material shall be applied to the pavement surface or to the bottom of the recessed groove as specified on the plans only when the air temperature is 50 °F (10 °C) or above and rising and the pavement temperature is 70 °F (21 °C) or greater. However, standard application of preformed plastic pavement markings will not be allowed after October 15. Adhesive shall be required.”

Revise the first paragraph of Article 780.12 of the Standard Specifications to read:

“**780.12 Inspection.** The epoxy, thermoplastic, preformed thermoplastic, preformed plastic Type B, C, or D, and polyurea pavement markings will be inspected following installation, but no later than October 15 for preformed plastic markings, November 1 for thermoplastic and preformed thermoplastic markings, and December 15 for epoxy and polyurea markings. In addition, they will be inspected following a winter performance period that extends 180 days from November 1.”

Revise the ninth paragraph of Article 780.12 of the Standard Specifications to read:

“This performance inspection and performance acceptance of the epoxy, thermoplastic, preformed thermoplastic, preformed plastic Type B, C, or D, and polyurea markings shall not delay acceptance of the entire project and final payment due if the Contractor requires and receives from the subcontractor a third party "performance" bond naming the Department as obligee in the full amount of all pavement marking quantities listed in the contract, multiplied by the contract unit price. The bond shall be executed prior to acceptance and final payment of the non-pavement marking items and shall be in full force and effect until final performance inspection and performance acceptance of the epoxy, thermoplastic, preformed thermoplastic, preformed plastic, and polyurea pavement markings. Execution of the third party bond shall be the option of the Contractor.”

Revise the first paragraph of Article 780.14 of the Standard Specifications to read:

“780.14 Basis of Payment. This work will be paid for at the contract unit prices per foot (meter) of applied line width, as specified, for THERMOPLASTIC PAVEMENT MARKING - LINE; PAINT PAVEMENT MARKING - LINE; EPOXY PAVEMENT MARKING - LINE; PREFORMED PLASTIC PAVEMENT MARKING - LINE - TYPE B, C, D, or B – INLAID; PREFORMED THERMOPLASTIC PAVEMENT MARKING – LINE, POLYUREA PAVEMENT MARKING TYPE I – LINE, POLYUREA PAVEMENT MARKING TYPE II - LINE; and/or per square foot (square meter) for THERMOPLASTIC PAVEMENT MARKING - LETTERS AND SYMBOLS; PAINT PAVEMENT MARKING - LETTERS AND SYMBOLS; EPOXY PAVEMENT MARKING - LETTERS AND SYMBOLS; PREFORMED PLASTIC PAVEMENT MARKING - TYPE B, C, D, or B – INLAID - LETTERS AND SYMBOLS; PREFORMED THERMOPLASTIC PAVEMENT MARKING - LETTERS AND SYMBOLS.”

Add the following to Section 1095 of the Standard Specifications:

“1095.10 Preformed Plastic Pavement Marking, Type D. The preformed patterned markings shall consist of a white or yellow tape with wet retroreflective media incorporated to provide immediate and continuing retroreflection during both wet and dry conditions. The pavement marking shall be manufactured without the use of heavy metals including lead chromate pigments or other similar, lead-containing chemicals.

The white and yellow preformed plastic pavement markings shall meet the Type B requirements of Article 1095.03(b), (c), (d), (e), (i), (l), (m), (n) and the following.

- (a) Composition. The pliant polymer pavement markings shall consist of a mixture of high-quality polymeric materials, pigments and glass beads distributed throughout its base cross-sectional area, with a layer of wet retroreflective media bonded to a durable polyurethane topcoat surface. The patterned surface shall have approximately 40% ± 10% of the surface area raised and presenting a near vertical face to traffic from any direction. The channels between the raised areas shall be substantially free of exposed beads or particles.
- (b) Retroreflectance. The white and yellow markings shall meet the following for initial dry and wet retroreflectance.
 - (1) Dry Retroreflectance. Dry retroreflectance shall be measured under dry conditions according to ASTM D4061 and meet the values described in Article 1095.03(l) for Type B.
 - (2) Wet Retroreflectance. Wet retroreflectance shall be measured under wet conditions according to ASTM E2177 and meet the values shown in the following table.

Wet Retroreflectance, Initial R_L	
Color	R_L 1.05/88.76
White	300
Yellow	200

- (c) Color. The material shall meet the following requirements for daylight reflectance and color, when tested, using a color spectrophotometer with 45 degrees circumferential/zero degree geometry, illuminant D65, and a two degree observer angle. The color instrument shall measure the visible spectrum from 380 to 720 nm with a wavelength measurement interval and spectral bandpass of 10 nm.

Color	Daylight Reflectance %Y
White	65 minimum
*Yellow	36-59

*Shall match Federal 595 Color No. 33538 and the chromaticity limits as follows.

x	0.490	0.475	0.485	0.530
y	0.470	0.438	0.425	0.456

- (d) Sampling, Testing, Acceptance, and Certification. Prior to approval and use of the preformed pavement marking materials, the manufacturer shall submit a notarized certification from an independent laboratory, together with the results of all tests, stating that the material meets the requirements as set forth herein. The certification test report shall state the lot tested, manufacturer's name, and date of manufacture.

After approval by the Department, samples and certification by the manufacturer shall be submitted for each batch used. The manufacturer shall submit a certification stating that the material meets the requirements as set forth herein and is essentially identical to the material sent for qualification. The certification shall state the lot tested, manufacturer's name, and date of manufacture."