

January 10, 2022

SUBJECT: Route MS 6055 (Williamson County Parkway) Section 19-00124-00-SP (City of Marion) Williamson County Contract No. 99634 Item 121 January 21, 2022 Letting Addendum (C)

NOTICE TO PROSPECTIVE BIDDERS:

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

1. Revised page 23 of the Special Provisions.

Prime contractors must utilize the enclosed material when preparing their bid and must include any changes to the Schedule of Prices in their bid.

Very truly yours,

TELEG

Jack A. Elston, P.E. Bureau Chief, Design and Environment

density verification locations. The Engineer will test the cores collected by the Contractor for density according to Illinois Modified AASHTO T 166 or AASHTO T 275.

If nuclear density gauge testing is the density verification method, the Engineer will conduct nuclear density gauge tests. The Engineer will follow the density testing procedure detailed in the document "Illinois Modified ASTM D 2950, Standard Test Method for Density of Bituminous Concrete In-Place by Nuclear Method".

A density verification test will be the result of a single core or the average of the nuclear density tests at one location. The results of each density test must be within acceptable limits. The Engineer will promptly notify the Contractor of observed deficiencies."

Revise the seventh paragraph and all subsequent paragraphs in Section D. of the document "Hot-Mix Asphalt QC/QA Initial Daily Plant and Random Samples" to read:

\^

"Mixtures shall be sampled from the truck at the plant by the Contractor following the same procedure used to collect QC mixture samples (Section A). This process will be witnessed by the Engineer who will take custody of the verification sample. Each sample bag with a verification mixture sample will be secured by the Engineer using a locking ID tag. Sample boxes containing the verification mixture sample will be sealed/taped by the Engineer using a security ID label."

IIXTURE DESIGN TAB	LE
ocations	Hot Mix Asphalt Surface Course
vlixture Use(s)	Hot Mix Asphalt Surface Course, Mix D, N70
AB/PG	SBS PG 76-22
ABR % (Max)	As per Article 1031.06 (c)
Design Air Voids	4%, 70 Gyration Design
Vixture Composition (Gradation Vixture)	IL 9.5FG
Friction Aggregate	D Surface
vlixture Weight	112 lbs/Sq Yd/In
Quality Management Program	QC/QA
Sublot Size	NA

3 REVISED 1/7/2022

SP 2