

May 27, 2014

SUBJECT: Various Routes Project M-4003(278) Section 14-00082-00-RS (Westchester) Cook County Contract No. 61A44 Item No. 201, June 13, 2014 Letting Addendum A

NOTICE TO PROSPECTIVE BIDDERS:

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

- 1. Revised Table of Contents and pages 19-23 of the special provisions.
- 2. Revised plan sheet 5

Prime contractors must utilize the enclosed material when preparing their bid and must include any Schedule of Prices changes in their bidding proposal.

Bidders using computer-generated bids are cautioned to reflect any and all Schedule of Prices changes, if involved, into their computer programs.

Very truly yours,

John Baranzelli, P.E. Acting Engineer of Design and Environment

Jot Dalechayan DE.

By: Ted B. Walschleger, P. E. Engineer of Project Management

#### TABLE OF CONTENTS PROJECT SPECIFIC SPECIAL PROVISIONS

.

ITEM	PAGE
LOCATION OF PROJECT	1
DESCRIPTION OF PROJECT	
NOTIFICATION OF RESIDENTS	
STATUS OF UTILITIES TO BE ADJUSTED.	
MAINTENANCE OF ROADWAYS	
ITEMS TO BE SALVAGED	
FRAMES AND LIDS, TYPE 1	
FRAMES AND LIDS TO BE ADJUSTED (SPECIAL)	3
VALVE BOXES TO BE ADJUSTED (SPECIAL)	лЭ Д
MANHOLES TO BE RECONSTRUCTED	
PRECAST CONCRETE SECTION S FOR STRUCTURES	
CONNECTION OF DISSIMILAR PIPE MATERIALS	
AGGREGATE BEDDING FOR CONCRETE WORK	
SIDEWALK AND DRIVEWAY PAVEMENT REMOVAL	
PORTLAND CEMENT CONCRETE SIDEWALK, 5 INCH	
COMBINATION CONCRETE CURB AND GUTTER REMOVAL	
COMBINATION CONCRETE CURB AND GUTTER, TYPE	0
B-6.12 (MODIFIED)	6
DETECTABLE WARNINGS	0 7
CURING AND PROTECTION	
CURB AND GUTTER TRANSITIONS	
HOT-MIX ASPHALT PAVING OPERATIONS	
LIMITATION OF OPERATIONS	
CLASS D PATCHES	
TRAFFIC CONTROL PLAN	
HOT-MIX ASPHALT SURFACE REMOVAL, VARIABLE DEPTH	Q
ADJUSTMENTS AND RECONSTRUCTIONS (D1)	10
COARSE AGGREGATE FOR BACKFILL, TRENCH BACKFILL, AND BEDDING (D1)	11
DRAINAGE AND INLET PROTECTION UNDER TRAFFIC (D1)	
FINE AGGREGATE FOR HOT-MIX ASPHALT (HMA) (D1)	
FRICTION SURFACE AGGREGATE (D1)	13
GROUND TIRE RUBBER (GTR) MODIFIED ASPHALT BINDER (D1)	16
HOT MIX ASPHALT MIXTURES, EGA MODIFIED PERFORMANCE GRADED (PG)	10
ASPHALT BINDER (D1)	17
HOT-MIX ASPHALT MIXTURE IL-4.75 (D1)	
HOT MIX ASPHALT QUALITY CONTROL FOR PERFORMANCE (BMPR)	
HMA MIXTURE DESIGN REQUIREMENTS (D1)	23
HOT MIX ASPHALT- PRIME COAT (D-1)	28
PUBLIC CONVENIENCE AND SAFETY (D1)	31
RECLAIMED ASPHALT PAVEMENT AND RECLAIMED ASPHALT SHINGLES (D1)	37
TEMPORARY INFORMATION SIGNING.	<u>41</u>
TRAFFIC SIGNAL SPECIFICATIONS FOR DETECTOR REPLACEMENT AND/OR	*** * *
INSTALLATION ON ROADWAY GRINDING, RESURFACING, & PATCHING OPERATIONS	
(D1)	42

LR 105 LR 107-4 BDE SPECIAL PROVISIONS

.

i

Mixture Production. Plant modifications may be required to accommodate the addition of higher percentages of mineral filler as required by the JMF.

During production, mineral filler shall not be stored in the same silo as collected dust. This may require any previously collected bag house dust in a storage silo prior to production of the IL-4.75 mixture to be wasted. Only metered bag house dust may be returned back directly to the mix. Any additional minus No. 200 (75  $\mu$ m) material needed to produce the IL-4.75 shall be mineral filler.

As an option, collected bag-house dust may be used in lieu of manufactured mineral filler, provided; 1) there is enough available for the production of the IL-4.75 mix for the entire project and 2) a mix design was prepared with collected bag-house dust.

The mixture shall be produced within the temperature range recommended by the asphalt cement producer; but not less than 325 °F (165 °C).

The amount of moisture remaining in the finished mixture (at silo discharge) shall be less than 0.3 percent based on the weight of the test sample after drying.

Mixtures contain steel slag sand or aggregate having absorptions  $\geq 2.5$  percent shall have a silo storage plus haul time of not less than 1.5 hours.

Placement.

Revise Article 406.06 (b) (2) a. to read as follows:

"a. The surface shall be dry for at least 12 hours, and clean, prior to placement of the mixture.

As an option, the contractor will be allowed to use a heated drier, at no additional cost to the Department, to expedite the drying of the pavement. No mix will be placed in areas of standing water or areas that show evidence of moisture or dampness. The use of a heated drier will be stopped if the pavement shows signs of damaged."

# HOT MIX ASPHALT QUALITY CONTROL FOR PERFORMANCE (BMPR)

Effective: January 1, 2012 Revised: December 1, 2013

<u>Description</u>. This special provision describes the procedures for production, placement and payment of hot-mix asphalt (HMA). This work shall be according to the Standard Specifications except as modified herein. This special provision shall apply to HMA mixtures as listed in the following table.

Mixture/Use:	HMA Surface Course, Mix "D", N50 (IL 9.5mm) /
	Finish surface course on roadway
Location:	Enterprise Drive(Station 2+00 to Station 34+62)
	and Constitution Drive (Station 1+00 to Station
	14+05) from Wolf Road to Cermak Road

Exceptions may be approved for small tonnage less than 800 (725 metric) tons and miscellaneous mixture applications as defined by the Engineer.

Delete Articles: 406.06(b)(1), 2<sup>nd</sup> Paragraph (Temperature requirements)

406.06 (e), 3 <sup>rd</sup> Paragraph (Pavers speed requirements)
406.07 (Compaction)
1030.05(a)(4, 5, 9,) (QC/QA Documents)
1030.05(d)(2)a. (Plant Tests)
1030.05(d)(2)b. (Dust-to-Asphalt and Moisture Content)
1030.05(d)(2)d. (Small Connage)
1030.05(d)(2)f. (HMA Sampling)
1030.05(d)(3) (Required Field Tests)
1030.05(d)(4) (Control Limits)
1030.05(d)(5) (Control Charts)
1030.05(d)(7) (Corrective Action for Field Tests (Density))
1030.05(e) (Quality Assurance by the Engineer)
1030.05(f) (Acceptance by the Engineer)
1030.06(a), 3rd paragraph (Before start-up)
1030.06(a), 7 <sup>th</sup> paragraph (After an acceptable)
1030.06(a) 8 <sup>th</sup> paragraph (If a mixture)
1030.06(a), 9 <sup>th</sup> paragraph (A nuclear/core)

#### Definitions:

- (a) Quality Control (QC): All production and construction activities by the Contractor required to achieve the required level of quality.
- (b) Quality Assurance (QA): All monitoring and testing activities by the Engineer required to assess product quality, level of payment, and acceptability of the product.
- (c) Pay Parameters: Pay Parameters shall be field Voids in the Mineral Aggregate (VMA), voids, and density. Field VMA will be calculated using the combined aggregates bulk specific gravity (G<sub>sb</sub>) from the mix design.
- (d) Mixture Lot. A lot shall begin once an acceptable test strip has been completed and the AJMF has been determined. If the test strip is waived, a sublot shall begin with the start of production. A mixture lot shall consist of four sublots unless it is the last or only lot, in which case it may consist of as few as one sublot

- Mixture Sublot. A mixture sublot for field VMA, voids, and Dust/AC will be a maximum of 1000 tons (910 netric tons).
  - If the remaining quantity is greater than 200 but less than 1000 tons, a sublot will consist of that amount.
  - If the remaining quantity is less than or equal to 200 tons, the quantity shall be combined with the previous sublot.
- (f) Density Interval. Density Intervals shall be every 0.2 mile (320 m) for lift thickness equal to or less than 3 in. (75 mm) and 0.1 mile (160 m) for lift thickness greater than 3 in. (75 mm).
- (g) Density Sublot. A sublot for density shall be the average of five consecutive Density Intervals. If a Density Interval is less than 200 ft (60 m), it will be combined with the previous Density Intervals.
  - If one or two Density Intervals remain outside a sublot, they shall be included in the previous sublot.
  - If three or more Density Intervals remain, they shall be considered a sublot.
- (h) Density Test: A density test consists of a core taken at a random longitudinal and random transverse offset within each Density Interval. The HMA maximum theoretical gravity (G<sub>mm</sub>) will be based on the running average of four Department test results. Initial G<sub>mm</sub> will be based on the average of the first four test results. If less than four G<sub>mm</sub> results are available, use an average of all available Department G<sub>mm</sub> test results.

The random transverse offset excludes a distance from each outer edge equal to the lift thickness or a minimum of 4 in. (100 mm). If a core is located within one foot of an unconfined edge, 2.0 percent density will be added to the density of that core.

# Quality Control (QC) by the Contractor:

The Contractor's QC plan shall include the schedule of testing for both pay parameters and non-pay parameters required to control the product such as asphalt binder content and mixture gradation. The minimum test frequency shall be according to the following table.

Quality	Characteristic	Minimum Test Frequenc	y V
Mixtu	re Gradation	· · · · · · · · · · · · · · · · · · ·	
Asphalt	Binder Content		
Dus	t/AC Ratio	1 per sublot	
Fi	eld VMA	-	
Voids	G <sub>mb</sub>		
VUIUS	G <sub>mm</sub>		

The Contractor's splits in conjunction with other quality control tests shall be used to control production.

201500 5-27-14

The Contractor shall submit split jobsite mix sample test results to the Engineer within 48 hours of the time of sampling. All QC testing shall be performed in a qualified laboratory by personnel who have successfully completed the Department's HMA Level I training.

### Quality Assurance (QA) by the Engineer:

Voids, field VMA and Dust/AC ratio: The Engineer will determine the random tonnage and the Contractor shall be responsible for obtaining the sample according to the "PFP Hot-Mix Asphalt Random Jobsite Sampling" procedure.

Density: The Engineer will identify the random locations for each density testing interval. The Contractor shall be responsible for obtaining the four inch cores within the same day and prior to opening to traffic unless otherwise approved by the Engineer according to the "PFP and QCP Random Density Procedure". The locations will be identified after final rolling and cores shall be obtained under the supervision of the Engineer. All core holes shall be filled immediately upon completion of coring. All water shall be removed from the core holes prior to filling. All core holes shall be filled with a rapid hardening mortar or concrete which shall be mixed in a separate container prior to placement in the hole. Any depressions in the surface of the filled core holes greater than 1/4 inch at the time of final inspection will require removal of the fill material to the depth of the lift thickness and replacement.

The Engineer will witness and secure all mixture and density samples. The Contractor shall transport the secured sample to a location designated by the Engineer.

The Engineer will test one or all of the randomly selected split samples from each lot for voids, field VMA and dust/AC ratio. The Engineer will test a minimum of one sample per project. The Engineer will test all of the pavement cores for density. All QA testing will be performed in aqualified laboratory by personnel who have successfully completed the Department's MMA Level I training. QA test results will be available to the Contractor within 10 working days from receipt of secured cores and split mixture samples.

The Engineer will maintain a complete record of all Department test results and copies will be provided to the Contractor with each set of subject results. The records will contain, as a minimum, the originals of all Department test results and raw data, random numbers used and resulting calculations for sampling locations, and quality level analysis calculations.

If the QA results do not meet the 100% sublot pay factor limits or do not compare to QC results within the precision limits listed below, the Engineer will test all split mix samples for the lot.

Test Parameter	Limits of Precision
G <sub>mb</sub>	0.030
G <sub>mm</sub>	0.026
Field VMA	1.0 %

Acceptance by the Engineer: All of the Department's tests shall be within the acceptable limits listed below:

Nevised 5-27-14

Parameter	•	Acceptable Limits
Field VMA		-1.0 - +3.0%1/
Voids		2.0-6.0%
Density:	IL-9.5, IL-12.5, IL-19.0, IL-25.0, IL-4.75, IL-9.5FG <sup>3/</sup>	90.0 - 98.0%
	SMA	92.0-98.0%
Dust / AC I	Ratio	$0.4 - 1.6^{2/}$

- 1/ Based on minimum required VMA from mix design
- 2/ Does not apply to SMA
- 3/ Acceptable density limits for IL-95FG placed less than 1.25 in. shall be 89.0% 98.0%

In addition, no visible pavement distresses shall be present such as, but not limited to, segregation, excessive coarse aggregate fracturing or flushing.

Basis of Payment: Payment will be based on the calculation of the Composite Pay Factor using QA results for each mix according to the "QCP Payment Calculation" document.

<u>Dust / AC Ratio</u>. A monetary deduction will be made using the pay adjustment table below for dust/AC ratios that deviate from the 0.6 to 1.2 range. If the tested sublot is outside of this range, the Department will test the remaining sublots for Dust / AC pay adjustment.

and the second se	Range	Deduct / sublot	
	$0.6 \le X \le 1.2$	\$0	
	$0.5 \le X \le 0.6$ or $1.2 \le X \le 1.4$	\$1000	
	$0.4 \le X < 0.5$ or $1.4 \le X \le 1.6$	\$3000	
	X < 0.4 or $X > 1.6$	Shall be removed and replaced	

# HMA MIXTURE DESIGN REQUIREMENTS (D-1)

Effective: January 1, 2013 Revised: November 1, 2013

Revise Article 406.14(b) of the Standard Specifications to read.

"(b) If the HMA placed during the initial test strip (1) is determined to be unacceptable to remain in place by the Engineer, and (2) was not produced within 2.0 to 6.0 percent air voids or within the individual control limits of the JMF, the mixture and test strip will not be paid for and the mixture shall be removed at the Contractor's expense. An additional test strip and mixture will be paid for in full, if produced within 2.0 to 6.0 percent air voids and within the individual control limits of the JMF."

Revise Article 406.14(c) of the Standard Specifications to read.