ASBESTOS SURVEY REPORT

PTB 196-032
Asbestos Survey for Building Demolition (I-80)
220 Duncan Street, Joliet, Illinois
Region One/District One

Prepared for:

Illinois Department of Transportation
District 1

Submitted to:

WSP USA
30 N. LaSalle Street
Chicago, IL, 60602

Prepared by:

GSG CONSULTANTS, INC.
735 Remington Road, Schaumburg IL 60173
Tel: 630.994.2600, www.gsg-consultants.com

August 8, 2025

GSG CONSULTANTS, INC.

735 Remington Road
Schaumburg, IL 60173
Tel: 630.994.2600
www.gsg-consultants.com

August 8, 2025

David Skaleski, P.E.
Project Manager
WSP USA
30 N. LaSalle Street, Suite 4200
Chicago, Illinois 60602

Asbestos Survey Report
PTB 198-003
FAI-80 (I-80) over Des Plaines River Bridge
Job N. D-91-204-19
220 Duncan Street, Joliet, IL
Parcel No. 1P10168

Dear Mr. Skaleski:

GSG Consultants Inc has conducted an Asbestos Survey for the above referenced property in accordance with our contractual agreement. The report provides a description of the site, survey methodology, analytical results, abatement cost estimates, and recommendations.

Should you have any questions or require additional information, please call us at 630-994-2600.

Prepared by: epahomi — August 8, 2025
Erin Pahomi — Date
Asbestos Building Inspector
Inspector License No: 100-20674

Reviewed By: Vincent Gee — August 8, 2025
Vince Gee, M.S. — Date
Senior Project Manager

QA Manager: Ala Sassila — August 8, 2025
Ala E Sassila, Ph.D., PE — Date

TABLE OF CONTENTS

1.0 INTRODUCTION 4
2.0 SURVEY METHODOLOGY 5
2.1 VISUAL INSPECTION 5
2.2 SAMPLING PROCEDURES 6
2.3 QUANTIFICATION 6
3.0 ANALYTICAL RESULTS 8
3.1 TESTING PROCEDURES 8
3.2 FINDINGS 8
4.0 RECOMMENDATIONS 9
5.0 LIMITATIONS 11
6.0 CERTIFICATION 12

TABLES

Table 1 Materials Sampled for ACM 2

EXHIBITS

Figure 1 Asbestos Bulk Sampling Locations
Figure 2 Asbestos-Containing Materials Locations

APPENDICES

Appendix A Analytical Testing Results
Appendix B Reference Photographs
Appendix C Inspector Licenses and Training Certificates
Appendix D Laboratory Accreditations

ACRONYMS AND ABBREVIATIONS

ACM	**Asbestos-Containing Materials**
ACBM	**Asbestos-Containing Building Materials**
AHERA	**Asbestos Hazard Emergency Response Act**
CFR	**Code of Federal Regulations**
COC	**Chain of Custody**
GSG	**GSG Consultants, Inc.**
IDOT	**Illinois Department of Transportation**
IDPH	**Illinois Department of Public Health**
NESHAP	**National Emissions Standards for Hazardous Air Pollutant**
NVLAP	**National Voluntary Laboratory Accreditation Program**
OSHA	**Occupational Safety and Health Administration**
PLM	**Polarized Light Microscopy**
RACM	**Regulated Asbestos-Containing Material**
TSI	**Thermal System Insulation**
USEPA	**United States Environmental Protection Agency**

SURVEY SUMMARY

SITE INFORMATION			
FAP Route: County: Section: IDOT Job No. Parcel No.	FAI-80 (I-80) Will N/A D-91-204-19 1P10168	Address: City, State, Zip Property Type: Construction Date: Building Size:	220 Duncan Street Joliet, IL 60433 Single-Family Residential 1900 710 SF

ASBESTOS CONTAINING MATERIALS		
Survey Date:	July 22, 2025	
Weather Conditions:	87°F, Sunny	
By Whom: Firm: Inspector: IDPH License No.	 GSG Consultants, Inc Tim Walsh 100-08900	
Results:	Number of Material Types Sampled Number of Samples Collected: Number of Materials Tested Positive: Was Friable ACM Found? Were Roofing Materials Sampled? Are There Unique State or Local Requirements?	**14** **42** **3** **Yes** **Yes** **No**
Laboratory Used:	Name: Sterling Labs Address: 2242 W. Harrison Street, Chicago, Illinois NVLAP: 101202-0	
Building Access Limitations:	None	

ASBESTOS-CONTAINING MATERIALS (ACM) SURVEY RESULTS:

Parcel No. 1P10168
Residential Property
220 Duncan Street, Joliet, Illinois

Table 1 provides a list of the homogeneous building material types that were sampled as part of the asbestos survey and the laboratory testing results.

HA No.	Material Description	Location	Type[1]	Condition	Friable	% Asbestos*	# of Samples	Estimated Quantity [2]
1	12"x12" White Floor Tile	Kitchen, Bathroom	Misc.	Good	No	ND	3	N/A
2	12"x12" White Floor Tile Mastic	Kitchen, Bathroom	Misc.	Good	No	ND	3	N/A
3	Plaster	Throughout	Misc.	Good	No	ND	3	N/A
4	Window Glazing	Throughout	Misc.	Good	No	ND	3	N/A
5	Chimney Brick	Roof	Misc.	Good	No	ND	3	N/A
6	**Pipe Insulation**	**Basement**	**TSI**	**Good**	**Yes**	**Chrysotile 10-15%**	**3**	**6 LF**
7	**Pipe Fittings**	**Basement**	**TSI**	**Good**	**Yes**	**Chrysotile 5-10%**	**3**	**2 LF**
8	**Duct Wrap**	**Basement**	**TSI**	**Good**	**Yes**	**Chrysotile 10-15%**	**3**	**25 SF**
9	1'x1' Ceiling Tile	Bedroom	Misc.	Good	No	ND	3	N/A
10	Roofing Material (3 Layers)	House	Misc.	Good	No	ND	3	N/A
11	Roofing Material (3 Layers)	Garage	Misc.	Good	No	ND	3	N/A
12	Exterior Window Caulk	Exterior	Misc.	Good	No	ND	3	N/A
13	Exterior Door Caulk	Exterior	Misc.	Good	No	ND	3	N/A
14	Exterior Siding	Exterior	Misc.	Good	No	ND	3	N/A
Total Estimated Quantity of ACM								25 SF/ 8 LF

(1) TSI= Thermal System Insulation, Surf. = Surfacing Material, and Misc. = Miscellaneous.
(2) Quantities are estimates only, all quantities must be field verified.

1.0 INTRODUCTION

GSG Consultants Inc. (GSG) conducted an Asbestos Survey at Parcel No. 1P10168 located at 220 Duncan Street in Joliet, Illinois. The site is improved with a one-story, single-family house with an attic and a detached garage. The house was constructed in 1900 and is approximately 710 square feet in size with an unfinished basement and an asphalt shingled roof. The interior walls and ceilings are drywall, plaster, and ceiling tile, and the floors are floor tile and wood. The building exterior is masonry and aluminum over wood siding.

GSG conducted the asbestos survey to satisfy requirements of the United States Environmental Protection Agency (USEPA) regulations under 40 CFR Part 61, Subpart M of the National Emission Standards for Hazardous Air Pollutants (NESHAP) and applicable state and local regulations. This was accomplished by conducting a visual inspection of the structures to be impacted by the planned demolition and collecting samples of suspect ACM based on these observations.

The results, findings, conclusions, and recommendations expressed in this report are based on conditions observed during GSG's survey of the project area. The information contained in this report represents conditions at the time of the survey and may not accurately represent conditions at a later date. The conclusions in this report are based on conditions observed in accessible areas of the project area. The possibility exists that suspect hazardous building materials or conditions may exist within wall cavities, voids, or other areas hidden from view which were not observed and cannot be ruled out. Any additional potential hazardous building materials encountered that will be disturbed during the demolition activities and that differ from the materials assessed during this survey, were hidden from view, or were located in an area not accessible will require further sampling and analysis prior to disturbance. The estimated quantities provided herein should be considered approximate and are accurate to the extent allowable under the terms and conditions of our contract. This report has been prepared with generally accepted industry practices and procedures. No other warranty, either expressed or implied, is made.

The investigation did not include access or inspection of confined spaces, underground piping, conduits, and building footings, if any. Materials associated with electrical components and energized equipment were not safely accessible and were not sampled.

2.0 SURVEY METHODOLOGY

The asbestos survey was conducted in compliance with the United States Environmental Protection Agency (USEPA) National Emissions Standards for Hazardous Air Pollutants (NESHAPs), applicable State of Illinois and local asbestos regulations. NESHAP regulations defined regulated asbestos-containing material (RACM) as a friable asbestos material, a Category I non-friable ACM that has become friable, a Category I non-friable ACM that will be or has been subjected to sanding, grinding, cutting or abrading, or Category II non-friable ACM that has a high probability of becoming or has become crumbled, pulverized, or reduced to powder by the forces acting on it during demolition or renovation. The materials were then classified with regard to whether they are friable or non-friable and classified as Class I or Class II non-friable materials, using the following definitions.

- **Friable:** NESHAP defines a friable ACM as any material containing more than one percent (1%) asbestos, which, when dry, may be crumbled, pulverized, or reduced to powder by hand pressure, and includes previously non-friable material where previously non-friable material becomes damaged to the extent that it may be crumbled, pulverized, or reduced to powder by hand pressure.
- **Category I Non-friable ACM:** NESHAP defines a Category I non-friable ACM as packing, gaskets, resilient floor covering (except vinyl sheet flooring products that are considered friable), and asphalt roofing products that contain more than one (1) percent asbestos as determined using the method specified in **Appendix A**, Subpart F, 40 CFR Part 763, Section 1, Polarized Light Microscopy
- **Category II Non-friable ACM:** means any material, excluding Category I non-friable ACM, containing more than 1 percent asbestos as determined using the methods specified in **Appendix A**, Subpart F, 40 CFR Part 763, Section 1, Polarized Light Microscopy that, when dry, cannot be crumbled, pulverized, or reduced to powder by hand pressure.

The survey consisted of three major activities: visual inspection, sampling, and quantification of building materials. A brief description of each of the above elements is provided in the following sections.

2.1 Visual Inspection

The inspector conducted an initial building walkthrough to determine the presence and condition of suspect asbestos-containing materials (ACMs) that were accessible and/or exposed. The survey consisted of accessing accessible areas of the buildings to identify and quantify regulated RACM. The inspector identified homogeneous areas (HA) comprised of building materials that appear similar throughout in terms of color and texture and assumed date of installation. Materials that were similar in general appearance were grouped into homogeneous sampling areas. Following the EPA inspection protocol, each identified suspect homogeneous material was placed in one of the following EPA classifications:

1. Surfacing Materials (spray or trowel applied to building members)
2. Thermal System Insulation (materials generally applied to various mechanical systems)
3. Miscellaneous Materials (any materials which do not fit either of the above categories)

2.2 Sampling procedures

The asbestos inspector collected a representative number of samples from each HA. Building materials identified as concrete (not including cement panels or pipe and soft concrete), glass (including fiberglass), wood, masonry, metal, and plastic are not considered suspect ACM and were not sampled. The survey included destructive, intrusive, and/or exploratory testing unless specifically prohibited by IDOT. Destructive sampling is performed to identify materials that are concealed or obstructed. Concealed or obstructed areas include but are not limited to wall cavities, pipe chases, spaces above fixed ceilings, materials located under carpeting or subfloors, and ceramic tile grout/adhesive. Bulk samples of suspect ACM were collected in general accordance with Asbestos Hazard Emergency Response Act (AHERA) sampling protocols, based on the results of the visual observation. Random samples of suspect materials were collected of each HA.

A total of 42 bulk samples of suspect ACM, three (3) samples for each of the 14 homogeneous areas, were collected from various homogeneous areas of the buildings. Bulk samples were collected from the following materials/homogeneous area(s):

- 12”x12” White Floor Tile
- 12”x12” White Floor Tile Mastic
- Plaster
- Window Glazing
- Chimney Brick
- Pipe Insulation
- Pipe Fittings
- Duct Wrap
- 1’x1’ Ceiling Tile
- House Roofing Material (3 Layers)
- Garage Roofing Material (3 Layers)
- Exterior Window Caulk
- Exterior Door Caulk
- Exterior Siding

Exhibit 1, Suspect ACM Sample Locations, shows the approximate locations of the suspect ACM collected during the field survey. Samples were placed in new sealable containers and labeled with unique sample numbers using an indelible marker. All non-disposable sampling equipment was wet-wiped and cleaned before and after each use. Bulk material samples were collected in 4-milliliter plastic bags, and tightly sealed for transport to the laboratory. Bulk samples were submitted under a chain-of-custody (COC) protocol to Sterling Labs in Chicago, Illinois.

2.3 Quantification

The inspector estimated the quantities of accessible and/or exposed materials that were suspected of containing asbestos using a measuring wheel and/or visual estimation. Actual quantities may differ between visually

estimated values and physical measurements. The asbestos abatement contractor is responsible for verifying reported quantities of ACM.

3.0 ANALYTICAL RESULTS

3.1 Testing Procedures

Sterling Lab analyzed the bulk samples using polarized light microscopy (PLM) method with dispersion staining techniques per USEPA methodology "Method for the Determination of Asbestos in Bulk Building Materials, EPA/600/R-93/116, July 1993". This is a standard method of analysis in optical mineralogy and the currently accepted method for the determination of asbestos in bulk samples. A suspect material is immersed in a solution of known refractive index and subjected to illumination by polarized light. The characteristic color displays which enable mineral identification. It should be noted that some ACM may not be accurately identified and/or quantified by PLM. The percentage of asbestos applicable was determined by microscopic visual estimation. Sterling analyzed each layer of each sample, which means if multiple layers are detected in the same sample (i.e., roof field), each layer was analyzed, and a separate result was provided for each layer. If any of the sample results from a homogeneous group had a positive result, that homogeneous group was considered to be ACM. Sterling Labs is accredited under the National Voluntary Laboratory Accreditation Program (NVLAP Accreditation Number 101202-0). Refer to **Appendix D** for laboratory accreditations.

3.2 Findings

GSG identified a total of 14 HAs from which 42 samples were collected and analyzed. Results are summarized in **Table 1** and include a description of each material, location, material type, test results, and estimated quantity. Materials indicated to have a "negative" result were confirmed by PLM analysis to be non-asbestos-containing. The laboratory results are providedin **Appendix A** and reference photographs are included in **Appendix B**. The USEPA defines ACM as a material containing greater than 1% asbestos. Materials containing less than 1% asbestos are not regulated by the USEPA or the State of Illinois, but their disturbance is regulated by OSHA.

The following **HAs were confirmed** to be **ACM**:

- Pipe Insulation
- Pipe Fittings
- Duct Wrap

The laboratory reported that asbestos was Not Detected (ND) in the remaining bulk samples collected by GSG. **Exhibit 2, ACM Locations,** shows the approximate locations of ACMs present in the building.

4.0 RECOMMENDATIONS

GSG understands that the residential property will be demolished as part of the I-80 improvement project. ACMs identified at the site must be removed/manager in accordance with all federal, state, and local regulations governing asbestos. ACMs abatement and management are subject to the US Environmental Protection Agency (USEPA, the Occupational and Health Administration (OSHA), Illinois Department of Public Health (IDPH), the Illinois Environmental Protection Agency (Illinois EPA), and other applicable Federal, State, and Local Government regulations. The following regulations governing asbestos removal and disposal:

1. U.S. Environmental Protection Agency Regional National Emissions Standards for Hazardous Air Pollutants (NESHAP) (40 CFR Part 61 Subpart A and M).
2. U.S. Department of Transportation "Hazardous Substances Final Rule" 49 CFR 171 and 172, November 21, 1986, February 17, 1987.
3. U.S. Department of Labor Occupational Safety and Health Administration (OSHA) Asbestos Regulations (Code of Federal Regulations Title 29, Part 1910, Section 1910.1001 and Part 1926, Section 1926.1101).
4. State of Illinois, Commercial and Public Building Asbestos Abatement Act. Illinois Department of Public Health, Rules for Asbestos Abatement for Public and Private Schools and Commercial and Public Buildings in Illinois (77 IL Admin. Code 855).

All friable asbestos-containing building materials (ACBMs) identified shall be removed from any building(s) or other structures before demolition. Non-friable ACMs may be left in place, unless during demolition, the ACMs may become friable. If other suspect materials not referenced in this survey report, within or on the outside of the buildings, are identified, not listed in **Table 1**, such materials shall be assumed ACMs until the materials are inspected by a licensed asbestos inspector, sampled, and submitted for laboratory analysis.

GSG recommends the preparation of an asbestos abatement project design before any demolition. An asbestos abatement design plan and specifications should include information regarding the location of containments and barriers, type of sealant, and air sampling requirements and clearance during the asbestos abatement activities. The asbestos design plan and specifications shall be prepared and signed by an IDPH licensed asbestos project designer following Illinois regulations. Before starting any abatement activities, an Asbestos Abatement notification is required for all asbestos projects and must be applied for at least ten (10) working days before the start of the project. A building demolition notification is required for all demolition projects and must be applied for at least ten (10) working days before the start of the project.

Abatement and Emergency Response shall be conducted only by IDPH licensed asbestos abatement contractor(s) under the supervision of a licensed asbestos project manager in accordance with all applicable federal, state, and local regulations. Workers who abate or manage asbestos must receive the proper training and licensing. OSHA prescribes required personnel monitoring including air monitoring and medical monitoring (ref 29 CFR 1926.1101). Personnel protective equipment and procedures are also required.

All asbestos waste generated from the required pre-demolition removal activities during the project must be wetted before it is double bagged in 6-millimeter plastic bags and enclosed in a plastic, leak-tight container with a lid and proper labeling. Discharge no visible emissions to the outside air during the collection, processing, packaging, or transporting of any asbestos-containing waste material. Asbestos waste is a “special waste” in

Illinois. Asbestos-containing waste can only be disposed of in Subtitle D landfills that are designated to receive asbestos waste.

5.0 LIMITATIONS

This report has been prepared for the exclusive use of the Illinois Department of Transportation (IDOT) and its Design Section Engineer consultant. GSG warrants that the investigations and methodology reflect our best efforts based upon the prevailing standard of care in the environmental field. This assessment was limited to those materials which were readily visible and with limited demolition and removal of building components. Additional suspect materials may be located behind walls and ceilings. The survey is subject to the following limitations.

- The investigation did not include sampling on any system which may present a hazard to the inspection team such as energized electrical systems or within confined spaces
- Materials associated with electrical components and energized equipment were not safely accessible and were not sampled.
- Estimated quantities of the ACMs are based on observations during the field survey and additional materials may be concealed or were not accessible. Therefore, all estimated quantities shall be field verified by the abatement contractor.

6.0 CERTIFICATION

The undersigned hereby affirm that the conditions described herein are accurate to the best of our knowledge and belief and are subject to the limitations inherent in the investigative techniques used and any expressed limitations of this survey. Applicable licensing to perform the described survey activities was valid at the time of performance of services in accordance with applicable federal, state and local laws, rules, and regulations.

Inspection Performed By:

Tim Walsh	100-08900
Asbestos Inspector's Name	IDPH License Number
	8.7.2025
Asbestos Inspector's Signature	Date

EXHIBITS

Exhibit 1 **Suspect ACM Sample Location Plans**

Exhibit 2 **Asbestos-Containing Materials Location Plan**

EXHIBIT 1

SL-1, SL-2, and SL-3
Suspect ACM Sample Location Plans



BASEMENT
SCALE = N.T.S.

LEGEND

SUSPECT ACM SAMPLE LOCATIONS: TW072225-XX

BATCH NUMBER: 375658

RED SAMPLES TESTED POSITIVE FOR ASBESTOS

SUSPECT ASBESTOS-CONTAINING MATERIALS SAMPLE LOCATION PLAN

ASBESTOS SURVEY FOR BUILDING DEMOLITION (I-80)
220 DUNCAN STREET
JOLIET,IL,60433

GSG CONSULTANTS, INC.
735 E. REMINGTON RD, SCHAUMBURG, IL 60173
TEL: +1 630.994.3600 | WWW.GSG-CONSULTANTS.COM
ILLINOIS PROFESSIONAL DESIGN FIRM # 184-002852

DRAWN BY:	PROJECT:
EP	21-2007
CHECKED BY:	SCALE:
TC	NTS
DATE:	SHEET #:
8/6/2025	1 OF 3
SHEET NAME:	

SL-1



FIRST FLOOR
SCALE = N.T.S.

LEGEND

SUSPECT ACM SAMPLE LOCATIONS: TW072225-XX

BATCH NUMBER: 375658

BEDROOM

SUSPECT ASBESTOS-CONTAINING MATERIALS SAMPLE LOCATION PLAN

ASBESTOS SURVEY FOR BUILDING DEMOLITION (I-80)
220 DUNCAN STREET
JOLIET,IL,60433

GSG CONSULTANTS, INC.
738 E. ROBINSON RD, SCHAUMBURG, IL 60173
TEL: +1 630.924.2400 | WWW.GSG-CONSULTANTS.COM
ILLINOIS PROFESSIONAL DESIGN FIRM # 184-002852

DRAWN BY:	PROJECT:
EP	21-2007
CHECKED BY:	SCALE:
TC	NTS
DATE:	SHEET #:
8/6/2025	2 OF 3
SHEET NAME:	

SL-2



LEGEND

SUSPECT ACM SAMPLE LOCATIONS: TW072225-XX

BATCH NUMBER: 375658

SUSPECT ASBESTOS-CONTAINING MATERIALS SAMPLE LOCATION PLAN

ASBESTOS SURVEY FOR BUILDING DEMOLITION (I-80)
220 DUNCAN STREET
JOLIET, IL, 60433

GSG CONSULTANTS, INC.
738 E. REMINGTON RD. SCHAUMBURG, IL 60173
TEL: 1+630.924.2600 | WWW.GSG-CONSULTANTS.COM
ILLINOIS PROFESSIONAL DESIGN FIRM # 184-002852

DRAWN BY:	PROJECT:
EP	21-2007
CHECKED BY:	SCALE:
TC	NTS
DATE:	SHEET #:
8/6/2025	3 OF 3
SHEET NAME:	

SL-3

EXHIBIT 2

ACM-1
ACM Location Plan



BASEMENT
SCALE = N.T.S.

LEGEND

LOCATIONS OF ASBESTOS-CONTAINING MATERIALS

PIPE INSULATION/FITTINGS

DUCT WRAP

ASBESTOS-CONTAINING MATERIALS SAMPLE LOCATION PLAN

ASBESTOS SURVEY FOR BUILDING DEMOLITION (I-80)
220 DUNCAN STREET
JOLIET, IL, 60433

GSG CONSULTANTS, INC.
735 E. REMINGTON RD, SCHAUMBURG, IL 60173
TEL: +1 630.994.3600 | WWW.GSG-CONSULTANTS.COM
ILLINOIS PROFESSIONAL DESIGN FIRM# 184-002852

DRAWN BY:	PROJECT:
EP	21-2007
CHECKED BY:	SCALE:
TC	NTS
DATE:	SHEET #:
8/6/2025	1 OF 1
SHEET NAME:	

ACM-1

APPENDIX A

Analytical Testing Results

STAT Analysis Corporation
2242 West Harrison St., Suite 200, Chicago, IL 60612-3766
Tel: (312) 733-0551 Fax: (312) 733-2386 STATinfo@STATAnalysis.com

NVLAP Lab Code 101202-0

ASBESTOS ANALYSIS BY POLARIZED LIGHT MICROSCOPY

Method: EPA/600/R-93/116

GSG Consultants, Inc.
735 Remington Road
Schaumburg, IL 60173
Phone: (630) 994-2600
Fax: (312) 733-5612

Reference:
Location: 220 Duncan
Batch No.: 375658
Customer No.: 4651

Date Received: 07/28/2025
Date Analyzed: 08/04/2025
Date Reported: 08/04/2025
Turn Around Time: 5 Days

Laboratory Sample	Customer Sample Number	Asbestos Components (%)	Non-Asbestos Components (%)
375658001	TW072225-1	ND	Cellulose 1-5% Binder 95-99%
375658002	TW072225-2	ND	Cellulose 1-5% Binder 95-99%
375658003	TW072225-3	ND	Cellulose 1-5% Binder 95-99%
375658004	TW072225-4	ND	Cellulose 1-5% Binder 95-99%
375658005	TW072225-5	ND	Cellulose 1-5% Binder 95-99%
375658006	TW072225-6	ND	Cellulose 1-5% Binder 95-99%
375658007	TW072225-7	ND	Cellulose 1-5% Binder 95-99%
375658008	TW072225-8	ND	Cellulose 1-5% Binder 95-99%
375658009	TW072225-9	ND	Cellulose 1-5% Binder 95-99%
375658010	TW072225-10	ND	Cellulose 1-5% Binder 95-99%

ND = Asbestos Not Detected (Not Present) NA = Not Analyzed NS = Not Submitted

Components of inhomogeneous samples are analyzed per our Standard Operating Procedure, or per customer request.

The use of the NVLAP logo does not imply endorsement by NVLAP or any agency of the US Government.

Analyzed by Name : Daniel Mikos / Microscopist Date: 08/04/2025

STAT Analysis Corporation
2242 West Harrison St., Suite 200, Chicago, IL 60612-3766
Tel: (312) 733-0551 Fax: (312) 733-2386 STATinfo@STATAnalysis.com

NVLAP Lab Code 101202-0

ASBESTOS ANALYSIS BY POLARIZED LIGHT MICROSCOPY

Method: EPA/600/R-93/116

GSG Consultants, Inc.
735 Remington Road
Schaumburg, IL 60173
Phone: (630) 994-2600
Fax: (312) 733-5612

Reference:
Location: 220 Duncan
Batch No.: 375658
Customer No.: 4651

Date Received: 07/28/2025
Date Analyzed: 08/04/2025
Date Reported: 08/04/2025
Turn Around Time: 5 Days

Laboratory Sample	Customer Sample Number	Asbestos Components (%)	Non-Asbestos Components (%)
375658011	TW072225-11	ND	Cellulose 1-5% Binder 95-99%
375658012	TW072225-12	ND	Cellulose 1-5% Binder 95-99%
375658013	TW072225-13	ND	Cellulose 1-5% Binder 95-99%
375658014	TW072225-14	ND	Cellulose 1-5% Binder 95-99%
375658015	TW072225-15	ND	Cellulose 1-5% Binder 95-99%
375658016	TW072225-16	Chrysotile 10-15%	Binder 85-90%
375658017	TW072225-17	NA	
375658018	TW072225-18	NA	
375658019	TW072225-19	Chrysotile 5-10%	Binder 90-95%
375658020	TW072225-20	NA	
375658021	TW072225-21	NA	
375658022	TW072225-22	Chrysotile 10-15%	Binder 85-90%
375658023	TW072225-23	NA	
375658024	TW072225-24	NA	

ND = Asbestos Not Detected (Not Present) NA = Not Analyzed NS = Not Submitted

Components of inhomogeneous samples are analyzed per our Standard Operating Procedure, or per customer request.

The use of the NVLAP logo does not imply endorsement by NVLAP or any agency of the US Government.

Analyzed by Name : Daniel Mikos / Microscopist Date: 08/04/2025

STAT Analysis Corporation
2242 West Harrison St., Suite 200, Chicago, IL 60612-3766
Tel: (312) 733-0551 Fax: (312) 733-2386 STATinfo@STATAnalysis.com

NVLAP Lab Code 101202-0

ASBESTOS ANALYSIS BY POLARIZED LIGHT MICROSCOPY

Method: EPA/600/R-93/116

GSG Consultants, Inc.
735 Remington Road
Schaumburg, IL 60173
Phone: (630) 994-2600
Fax: (312) 733-5612

Reference:
Location: 220 Duncan
Batch No.: 375658
Customer No.: 4651

Date Received: 07/28/2025
Date Analyzed: 08/04/2025
Date Reported: 08/04/2025
Turn Around Time: 5 Days

Laboratory Sample	Customer Sample Number	Asbestos Components (%)	Non-Asbestos Components (%)
375658025	TW072225-25	ND	Cellulose 80-85% Binder 15-20%
375658026	TW072225-26	ND	Cellulose 80-85% Binder 15-20%
375658027	TW072225-27	ND	Cellulose 80-85% Binder 15-20%
375658028	TW072225-28BK	ND	Binder 85-90% Glass 10-15%
375658029	TW072225-29BK	ND	Binder 85-90% Glass 10-15%
375658030	TW072225-30BK	ND	Binder 85-90% Glass 10-15%
375658031	TW072225-28GY	ND	Binder 85-90% Glass 10-15%
375658032	TW072225-29GY	ND	Binder 85-90% Glass 10-15%
375658033	TW072225-30GY	ND	Binder 85-90% Glass 10-15%
375658034	TW072225-28BN	ND	Binder 85-90% Glass 10-15%

ND = Asbestos Not Detected (Not Present) NA = Not Analyzed NS = Not Submitted

Components of inhomogeneous samples are analyzed per our Standard Operating Procedure, or per customer request.

The use of the NVLAP logo does not imply endorsement by NVLAP or any agency of the US Government.

Analyzed by Name : Daniel Mikos / Microscopist Date: 08/04/2025

STAT Analysis Corporation
2242 West Harrison St., Suite 200, Chicago, IL 60612-3766
Tel: (312) 733-0551 Fax: (312) 733-2386 STATinfo@STATAnalysis.com

NVLAP Lab Code 101202-0

ASBESTOS ANALYSIS BY POLARIZED LIGHT MICROSCOPY

Method: EPA/600/R-93/116

GSG Consultants, Inc.
735 Remington Road
Schaumburg, IL 60173
Phone: (630) 994-2600
Fax: (312) 733-5612

Reference:
Location: 220 Duncan
Batch No.: 375658
Customer No.: 4651

Date Received: 07/28/2025
Date Analyzed: 08/04/2025
Date Reported: 08/04/2025
Turn Around Time: 5 Days

Laboratory Sample	Customer Sample Number	Asbestos Components (%)	Non-Asbestos Components (%)
375658035	TW072225-29BN	ND	Binder 85-90% Glass 10-15%
375658036	TW072225-30BN	ND	Binder 85-90% Glass 10-15%
375658037	TW072225-31GY	ND	Cellulose 10-15% Binder 85-90%
375658038	TW072225-32GY	ND	Cellulose 10-15% Binder 85-90%
375658039	TW072225-33GY	ND	Cellulose 10-15% Binder 85-90%
375658040	TW072225-31BK	ND	Cellulose 60-65% Binder 35-40%
375658041	TW072225-32BK	ND	Cellulose 60-65% Binder 35-40%
375658042	TW072225-33BK	ND	Cellulose 60-65% Binder 35-40%
375658043	TW072225-31BN	ND	Cellulose 10-15% Binder 85-90%
375658044	TW072225-32BN	ND	Cellulose 10-15% Binder 85-90%

ND = Asbestos Not Detected (Not Present) NA = Not Analyzed NS = Not Submitted

Components of inhomogeneous samples are analyzed per our Standard Operating Procedure, or per customer request.

The use of the NVLAP logo does not imply endorsement by NVLAP or any agency of the US Government.

Analyzed by Name :

Daniel Mikos / Microscopist

Date: 08/04/2025

STAT Analysis Corporation
2242 West Harrison St., Suite 200, Chicago, IL 60612-3766
Tel: (312) 733-0551 Fax: (312) 733-2386 STATinfo@STATAnalysis.com

NVLAP Lab Code 101202-0

ASBESTOS ANALYSIS BY POLARIZED LIGHT MICROSCOPY

Method: EPA/600/R-93/116

GSG Consultants, Inc.
735 Remington Road
Schaumburg, IL 60173
Phone: (630) 994-2600
Fax: (312) 733-5612

Reference:
Location: 220 Duncan
Batch No.: 375658
Customer No.: 4651

Date Received: 07/28/2025
Date Analyzed: 08/04/2025
Date Reported: 08/04/2025
Turn Around Time: 5 Days

Laboratory Sample	Customer Sample Number	Asbestos Components (%)	Non-Asbestos Components (%)
375658045	TW072225-33BN	ND	Cellulose 10-15% Binder 85-90%
375658046	TW072225-34	ND	Cellulose 1-5% Binder 95-99%
375658047	TW072225-35	ND	Cellulose 1-5% Binder 95-99%
375658048	TW072225-36	ND	Cellulose 1-5% Binder 95-99%
375658049	TW072225-37	ND	Cellulose 1-5% Binder 95-99%
375658050	TW072225-38	ND	Cellulose 1-5% Binder 95-99%
375658051	TW072225-39	ND	Cellulose 1-5% Binder 95-99%
375658052	TW072225-40	ND	Cellulose 10-15% Binder 85-90%
375658053	TW072225-41	ND	Cellulose 10-15% Binder 85-90%
375658054	TW072225-42	ND	Cellulose 10-15% Binder 85-90%

ND = Asbestos Not Detected (Not Present) NA = Not Analyzed NS = Not Submitted

Components of inhomogeneous samples are analyzed per our Standard Operating Procedure, or per customer request.

The use of the NVLAP logo does not imply endorsement by NVLAP or any agency of the US Government.

Analyzed by Name : Daniel Mikos / Microscopist

Date: 08/04/2025

GSG CONSULTANTS, INC.
Engineering and Industrial Hygiene Services
735 Remington Road
Schaumburg, IL 60173
(630) 994-2600 Fax: (312) 733-5612
www.gsg-consultants.com

375658

PLM BULK LABORATORY ANALYSIS FORM

Project Name:	**Project Manager:**
Project Number:	**Building Inspector:**
Project Address: 220 Duncan	**IDPH Number:**
City/ State:	**Work Day:** S M T W TH F S
Client:	**Analyze by Method:** EPA/600/R-93-116
Date: 7/22/25	

Field Number	HA Number	Type of material, specific sample location (i.e. Room Number, Building Construction Date)
TA072225- 1	HA-1	12x12 White Floor Tile Kitchen + Bath
2	↓	↓
3	↓	↓
4	HA-2	Mastic
5	↓	↓
6	↓	↓
7	HA-3	Plaster - Throughout
8	↓	↓
9	↓	↓
10	HA-4	Window Glazing
11	↓	↓
12	↓	↓
13	HA-5	Chimney Brick
14	↓	↓
15	↓	↓

TURN AROUND TIME:
1 Day
2 Days
3 Days
(5 Day) Other

COMMENTS: E-mail Results to:
twalsh@gsg-consultants.com
epahomi@gsg-consultants.com

STOP AT FIRST POSITIVE

CHAIN OF CUSTODY RECORD

Collected By(Signature)	Date: 7/22/25	Time:	Relinquished by (Signature)	Date: 7/25/25	Time:
Received by: (Signature)	Date:	Time:	Relinquished by: (signature)	Date:	Time:
Dispatched by: (Signature, if mailed)	Date:	Time:	Received for Laboratory by:	Date: 7/28/25	Time: 1600

Definitions: BLK-Bulk Sample, PLM-Polarized Light Microscopy, TEM-Transmission Electron Microscope.

GSG CONSULTANTS, INC.
Engineering and Industrial Hygiene Services
735 Remington Road
Schaumburg, IL 60173
(630) 994-2600 Fax: (312) 733-5612
www.gsg-consultants.com

375658

PLM BULK LABORATORY ANALYSIS FORM

Project Name:	**Project Manager:**
Project Number:	**Building Inspector:**
Project Address: 220 Duncan	**IDPH Number:**
City/ State:	**Work Day:** S M T W TH F S
Client:	**Analyze by Method:** EPA/600/R-93-116
Date: 7/22/25	

Field Number	HA Number	Type of material, specific sample location (i.e. Room Number, Building Construction Date)
TN072225-16	HA-6	Duo temp Pipe Insulation - Basement
17	↓	6 LF
18	↓	↓
19	HA-7	Fitting 2 Fittings
20	↓	↓
21	↓	↓
22	HA-8	Duct wrap 45 F
23	↓	↓
24	↓	↓
25	HA-9	1x1 Ceiling Tile
26	↓	↓ Bedroom off Kitchen
27	↓	↓
28	HA-10	Roofing Material - House
29	↓	↓ 3 Layers
30	↓	↓

TURN AROUND TIME:
1 Day
2 Days
3 Days
~~(5 Day)~~ **Other**

COMMENTS: E-mail Results to:
twalsh@gsg-consultants.com
epahomi@gsg-consultants.com

STOP AT FIRST POSITIVE

CHAIN OF CUSTODY RECORD

Collected By(Signature) TW	Date: 7/22/25	Time:	Relinquished by (Signature) TW	Date: 7/25/25	Time:
Received by: (Signature)	Date:	Time:	Relinquished by: (signature)	Date:	Time:
Dispatched by: (Signature, if mailed)	Date:	Time:	Received for Laboratory by:	Date: 7/25/25	Time: 16:00

Definitions: BLK-Bulk Sample, PLM-Polarized Light Microscopy, TEM-Transmission Electron Microscope.

GSG CONSULTANTS, INC.
Engineering and Industrial Hygiene Services
735 Remington Road
Schaumburg, IL 60173
(630) 994-2600 Fax: (312) 733-5612
www.gsg-consultants.com

375658

PLM BULK LABORATORY ANALYSIS FORM

Project Name:	**Project Manager:**
Project Number:	**Building Inspector:**
Project Address: 220 Duncan	**IDPH Number:**
City/ State:	**Work Day:** S M T W TH F S
Client:	**Analyze by Method:** EPA/600/R-93-116
Date: 7/22/25	

Field Number	HA Number	Type of material, specific sample location (i.e. Room Number, Building Construction Date)
TW072225-31	HA-11	Roofing Material - Garage
32	↓	3 Layers
33	↓	↓
34	HA-12	Exterior Window Caulk
35	↓	↓
36	↓	↓
37	HA-13	Exterior Door Caulk
38	↓	↓
39	↓	↓
40	HA-14	Exterior Siding
41	↓	↓
42	↓	↓
		Fiberglass Attic Insulation

TURN AROUND TIME:
1 Day
2 Days
3 Days
~~(5 Day)~~ Other

COMMENTS: E-mail Results to:
twalsh@gsg-consultants.com
epahomi@gsg-consultants.com

STOP AT FIRST POSITIVE

CHAIN OF CUSTODY RECORD

Collected By(Signature) TW	Date: 7/22/25	Time:	Relinquished by (Signature) TW	Date: 7/25/25	Time:
Received by: (Signature)	Date:	Time:	Relinquished by: (signature)	Date:	Time:
Dispatched by: (Signature, if mailed)	Date:	Time:	Received for Laboratory by: MP	Date: 7/25/25	Time: 16:00

Definitions: BLK-Bulk Sample, PLM-Polarized Light Microscopy, TEM-Transmission Electron Microscope.

APPENDIX B

Reference Photographs



Material Description:
Suspect ACM 12”x12” White Floor Tile & Mastic

Photo Location:
Kitchen

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Suspect ACM Plaster

Photo Location:
Living Room

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Suspect ACM window Glazing

Photo Location:
Living Room

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Suspect ACM Chimney Brick

Photo Location:
Basement

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Pipe Insulation Pipe & Fittings - **Tested Positive for Asbestos**

Photo Location:
Basement

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Duct Wrap - **Tested Positive for Asbestos**

Photo Location:
Basement

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Suspect ACM 1'x 1' Ceiling Tile

Photo Location:
Bedroom

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

Material Description:
Suspect ACM Roofing Material

Photo Location:
House Roof

ILLINOIS DEPARTMENT OF TRANSPORTATION **I-80 OVER DES PLAINES RIVER BRIDGE IMPROVEMENTS**	GSG Consultants, Inc. 735 Remington Road Schaumburg, Illinois 60173	**Date:** 7/22/2025

APPENDIX C

Inspector Licenses and Training Certifications

IDPH
ILLINOIS DEPARTMENT OF PUBLIC HEALTH

525-535 West Jefferson Street • Springfield, Illinois 62761-0001 • www.dph.illinois.gov

TIMOTHY WALSH
15237 LAPORTE AVE
OAK FOREST, IL 60452

4/22/2025

ASBESTOS PROFESSIONAL LICENSE ID NUMBER: 08900

Enclosed is your Asbestos Professional License. Please note the expiration date on the card and in the image depicted below.

COPY OF THE ASBESTOS PROFESSIONAL LICENSE

Front of License

IDPH

ASBESTOS PROFESSIONAL LICENSE

ID NUMBER	ISSUED	EXPIRES
100 - 08900	**4/22/2025**	**05/15/2026**

TIMOTHY WALSH
15237 LAPORTE AVE
OAK FOREST, IL 60452
Environmental Health

Back of License

ENDORSEMENTS	TC EXPIRES
INSPECTOR	1/18/2026
PROJECT MANAGER	10/2/2025
AIR SAMPLING PROFESSIONAL	

Alteration of this license shall result in legal action
This license issued under authority of the State of Illinois Department of Public Health
This license is valid only when accompanied by a valid training course certificate.

If you have any questions or need further assistance, contact the Asbestos Program at (217)782-3517 or fax (217)785-5897.

Our WEB address is: dph.illinois.gov/topics-services/environmental-health-protection/asbestos
EMAIL Address: dph.asbestos@illinois.gov

APPENDIX D

Laboratory Accreditations

United States Department of Commerce
National Institute of Standards and Technology

Certificate of Accreditation to ISO/IEC 17025:2017

NVLAP LAB CODE: 101202-0

STAT Analysis Corporation

Chicago, IL

is accredited by the National Voluntary Laboratory Accreditation Program for specific services, listed on the Scope of Accreditation, for:

Asbestos Fiber Analysis

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2017. This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communique on ISO/IEC 17025).

2025-07-01 through 2026-06-30

Effective Dates

For the National Voluntary Laboratory Accreditation Program

National Voluntary
Laboratory Accreditation Program

SCOPE OF ACCREDITATION TO ISO/IEC 17025:2017

STAT Analysis Corporation
Sterling Labs
2242 W. Harrison Suite 200
Chicago, IL 60612
Joseph Gusek
Phone: 312-733-0551
Email: jgusek@thesterlinglab.com
www.thesterlinglab.com

ASBESTOS FIBER ANALYSIS **NVLAP LAB CODE 101202-0**

Bulk Asbestos Analysis

Code	*Description*
18/A01	EPA -- 40 CFR Appendix E to Subpart E of Part 763, Interim Method of the Determination of Asbestos in Bulk Insulation Samples
18/A03	EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials

Airborne Asbestos Analysis

Code	*Description*
18/A02	U.S. EPA's "Interim Transmission Electron Microscopy Analytical Methods-Mandatory and Nonmandatory-and Mandatory Section to Determine Completion of Response Actions" as found in 40 CFR, Part 763, Subpart E, Appendix A.

For the National Voluntary Laboratory Accreditation Program